

# SCIENTIFIC INFORMATION

## (Aqua) Ionofil Plus – Technical Profile

Compressive strength	155 MPa	ISO 9917
Water solubility	0.37%	ISO 9917
Shear bond strength on dentine	5.5 MPa	
Radiopacity	> 200 %Al	ISO 9917
Working time	2.5 – 3.5 min	ISO 9917
Intraoral setting time	5 - 6 min	

The stated measurement values do not represent a specified value within the scope of the VOCO GmbH quality assurance system.