

SCIENTIFIC INFORMATION

Easy Glaze – Technical Profile

Density [g/ml]	1,09-1,10
Refractive index n_D^{20}	1,466-1,469
Curing depth (10 s light-curing, 500 mW/cm ²)	> 2.0 mm

The stated measurement values do not represent a specified value within the scope of the VOCO GmbH quality assurance system.