

# SCIENTIFIC INFORMATION

## Ionofil Plus AC – Technical Profile

Compressive strength	175 MPa	ISO 9917
Diametral tensile strength	16 MPa	
3-Point flexural strength	34 MPa	analogous ISO 4049
Radiopacity	200 %Al	ISO 9917
Working time	2 min	ISO 9917
Intraoral setting time	4 min	

The stated measurement values do not represent a specified value within the scope of the VOCO GmbH quality assurance system.