

# SCIENTIFIC INFORMATION

## Solobond M – Technical Profile

Shear bond strength on dentine	28.1 MPa	analogous Reinhardt*
Shear bond strength on enamel	32.0 MPa	analogous Reinhardt*

The stated measurement values do not represent a specified value within the scope of the VOCO GmbH quality assurance system.

\* Reinhardt KJ, *Phillip Journal* 3-4, 1997, 101-104.